



Dongguan Baoxu Chemical Technology, Ltd.

P:+86-0769-22821082 Fax:0769-22821083

Email:info@additivesforpolymer.com Web:www.additivesforpolymer.com

Room1118 Caijin Business Building Nancheng Distinct Guangdong China

Pigment Violet 19

There are γ -Modification and β -Modification in pigment violet 19.

γ -Modification shows better light and weather resistance than β -Modification and meet outdoor application.

γ -Modification are used in polyester,PVC,PC,Nylon,

β -Modification is often blend with other inorganic pigment of ferric oxide or molybdate red, or with organic pigment orange 36, after blending, a deep red color is achieved


Chemistry

Synonym name:C.I.Pigment Violet 19,P.V.19, PV 19, C.I.73900,quinacridone violet 19

CAS Number:1047-16-1

EU Number: 213-879-2


Chemical Family: Quinacridone



Chemical Structure

Application Data

Heat Resistance In HDPE



The information and statement herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility, Users should undertake sufficient verification and testing to determine the suitable for their own particular purpose of any information or products referred to herein. No warranty of fitness for a particular purpose is made.



Dongguan Baoxu Chemical Technology, Ltd.

P:+86-0769-22821082 Fax:0769-22821083

Email:info@additivesforpolymer.com Web:www.additivesforpolymer.com

Room1118 Caijin Business Building Nancheng Distinct Guangdong China

HDPE	Heat resistance	250
	Fastness to migration	5/nt
	Light Fastness FS/WR	7/7
	Weather Fastness FS/WR	4/3
	Warpage in HDPE	low
PVC	Fastness to migration	5/nt
	Light Fastness FS/WR	7/7
	Weather Fastness FS/WR	4/3
Application	Polyolefins (PP/HDPE/LDPE/LLDPE)	●
	PVC	●
	PUR	●
	Engineerings	-
	Styrenics	○
	Elastomer&Rubeer	●
	Fiber (PE/PP/PA)	○

- Suitable, ○ Limited suitability, – Not suitable, nt-Not tested *Specific information available on request

The information and statement herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility, Users should undertake sufficient verification and testing to determine the suitable for their own particular purpose of any information or products referred to herein. No warranty of fitness for a particular purpose is made.