

**HALS 783 / Tinuvin 783****Chemical Name:**

Formula	50%HALS 944+50%HALS 622
---------	-------------------------

Molecular Weight	2000-3100
------------------	-----------

Physical Properties:

Appearance	white to slightly yellow pastilles
------------	------------------------------------

Softening point	55°C-140°C
-----------------	------------

Flash point	192°C
-------------	-------

Applications:**>Synergistic mixture of oligomeric hindered amine stabilizers**

>HALS 783 is particularly well suited for LDPE,LLDPE, HDPE films, tapes and thick sections and for PP films. It is also the product of choice for thick sections where indirect food contact approval is required.

>It's concentrations range between 0.1 % and 1.5 %, depending on the substrate, processing conditions and application

Handling and safety:

>In accordance with good industrial practice, handle with care and avoid unnecessary personal contact. Avoid continuous or repetitive breathing of dust. Use only with adequate ventilation. Avoid dust formation and ignition sources

>For additional handling and toxicological information, please consult us for Maternal Safety Date Sheet

Package:

25kg per bag then into carton, 500kg per pallet.