


UV P

Chemical name:

2-(2H-Benzotriazol-2-yl)-p-cresol

Formula	C ₁₃ H ₁₁ N ₃ O
Molecular Weight	225
CAS#	2440-22-4



Specification:

Appearance	Yellow crystalline powder	
Melting point	128-133 °C	
boiling point	225C°	
Solubility (20°C)	Water	< 0.1
	MeOH	0.2
	EtOH	10
	Acetone	3
	CH ₂ Cl ₂	16
	Hexane	0.8

Application:

- >Particularly effective in styrenic polymers, PVC, unsaturated polyesters, polyurethanes, acrylic polymers, and polycarbonates.
- >UV P can be used alone or in a variety of blends and combinations with antioxidants or uv absorbers where often a synergistic performance is observed
- >Tinuvin P has FDA approval for use in a wide variety of food contact applications.
- >The use levels of UV P range between 0.10% and 1.0%, depending on substrate and performance requirements of the final application.

Handing and Safety:

- >In accordance with good industrial practice, handle with care and avoid unnecessary personal contact. Protect skin. Prevent contamination of the environment. Avoid dust formation and ignition sources.
- >For additional handing and toxicological information, please consult us for **Maternal Safety Date Sheet**

Package:

25kg per fiber drum, 9*3 layer 27drum per pallet, or according to requirements.