

UV Stabilizer

	Name	CAS No.	MR °C	Physical Form	Compare As	Application
Benzophenone	UV 531	1843-05-6	47-49	Pale yellow powder	Chimassorb 81	PVC/Coatings
Benzotriazole	UV P	2440-22-4	128-132	Pale yellow powder	Tinuvin P	PVC/PUR
	UV 234	70321-86-7	139.5-141	White powder	Tinuvin 234	Engineerings
	UV 1130	104810-48-2	/	Yellow liquid	Tinuvin 1130	Coatings
	UV 326	3896-11-5	> 138	Pale yellow powder	Tinuvin 326	General application
	UV 327	3864-99-1	151	Pale yellow powder	Tinuvin 327	General application
	UV 328	25973-55-1	> 138	Pale yellow powder	Tinuvin 328	General application
	UV 329	3147-75-9	101-106	White powder	Tinuvin 329	General application
	UV 360	103597-45-1	194-198	Pale yellow powder	Tinuvin 360	Engineerings
	UV 384-2	127519-17-9	/	Pale yellow liquid	Tinuvin 384-2	HP coatings
	UV 928	73936-91-1	108-110	Pale yellow powder	Tinuvin 928	HP coatings
Triazine and other	UV B75	/	/	Yellow liquid	Tinuvin B75	PU
	UV 1164	2725-22-6	89-91	Pale yellow powder	Tinuvin 1164	Engineerings
	UV 1577	147315-50-2	147-151	Pale yellow powder	Tinuvin 1577	Engineerings
	UV 2908	67845-93-6	55-65	White powder	Cyasorb UV 2908	PP/PE/PVC
	UV 312	23949-66-8	124-127	White powder	Tinuvin 312	PVC/UP/PUR
	UV 3638	18600-59-4	> 310	White powder	Cyasorb UV 3638	PET/PC
	UV 400	153519-44-9	/	Yellow liquid	Tinuvin 400	HP coatings
	UV 5050	127519-17-9	/	Yellow granules	Tinuvin 5050	Coatings/plastics
	UV 866	/	/	White powder	Tinuvin PUR 866	TPE/TPU
Light Stabilizer	HALS 119	106990-43-6	115-150	Light yellow granule	Chimassorb 119	Agricultural films
	HALS 123	12957-67-1	/	Light yellow liquid	Tinuvin 123	Coatings
	HALS 292	41556-26-7/ 82919-37-7	/	Light yellow liquid	Tinuvin 292	Coatings
	HALS 622	65447-77-0	50-70	White powder	Tinuvin 622	Polyolefins
	HALS 770	52829-07-9	80-85	White powder	Tinuvin 770	General application
	HALS 783	65447-77-0/	55-140	White granules	Tinuvin 783	Film/tapes
	HALS 791	70624-18-9	> 55	White granules	Tinuvin 791	PP thick products
	HALS 944	70624-18-9	105-135	White granules	Chimassorb 944	Films
	3808PP5	167078-06-0	135-159	Light yellow granules	Cyasorb 3808PP5	Polyolefins
3853PP5	167078-06-0	28 >	Light yellow granules	Cyasorb 3853PP5	Polyolefins	